


Oshenite[®] | TRACE MINERALS COMPARISON VERSUS MINED CALCIUM CARBONATE

Test	Calcite/Limestone	Oolitic Aragonite
Specific Gravity	2.7	2.8
Mohs Hardness	3	3.5-4
Crystal Structure	Trigonal	Orthorhombic
Surface Area	.55 m ² /g	1.82 m ² /g
Zeta Potential	-1.01mV to 11.55mV	-33.85mV to -6.65mV
Crystallinity	Low	High
Microporosity	Low	Very High

Mined Calcium Carbonate



Oshenite[®]

